

Panels raised and fielded - 15 mm Oak without polystyrene

Construction:

15 mm Laminated Oak
 Glued with waterproof adhesive

(Appr.750 kg/m³ - heat conductivity: 0,18 W/mK)

U-Value:

U-Value - W/m ² K	
15 mm	
3,97	

Heat conductivity is calculated on the basis of the practical heat conductivity of each included material - taken from data sheets and DS418, version 6, 2002. Also relating to EN 12524.

Weight:

Weight appr. Kg./m ²	
15 mm	
11,3	

Measure:

Min.: 120 x 250 mm - Max.: 1030 x 2300 mm

No warranty on panels lager than 400 mm in the width

Tolerances:


Width/Height: +/- 1 mm - Diagonal: +/- 1,5 mm - Thickness: +/- 0,8 mm

Section drawing:

Profile type 1




Profile type 2



Profile type 3



Profile type 4



Made: 10.03.14	Data sheet: PMN	Draw.: HMN
Revised:	Data sheet:	Draw.:

O.H.Industri A/S
 Smedevej 17
 DK - 7430 Ikast
 +45 9725 1200
www.ohindustri.com