

## Panels raised and fielded - 15 mm Pine without polystyrene

**Construction:**

15 mm Laminated pine  
 Glued with waterproof adhesive

( Appr.500 kg/m<sup>3</sup> - heat conductivity: 0,13 W/mK )

**U-Value:**

U-Value - W/m <sup>2</sup> K	
15 mm	
3,53	

Heat conductivity is calculated on the basis of the practical heat conductivity of each included material - taken from data sheets and DS418, version 6, 2002. Also relating to EN 12524.

**Weight:**

Weight appr. Kg./m <sup>2</sup>	
15 mm	
7,5	

**Measure:**

Min.: 120 x 250 mm - Max.: 1030 x 2300 mm

No warranty on panels lager than 400 mm in the width

**Tolerances:**


Width/Height: +/- 1 mm - Diagonal: +/- 1,5 mm - Thickness: +/- 0,8 mm

**Section drawing:**

Profile type 1




Profile type 2



Profile type 3



Profile type 4



Made: 10.03.14	Data sheet: PMN	Draw.: HMN
Revised:	Data sheet:	Draw.:

O.H.Industri A/S  
 Smedevej 17  
 DK - 7430 Ikast  
 +45 9725 1200  
[www.ohindustri.com](http://www.ohindustri.com)